

ECOFIX



5L

1L

As with all wood finishing always do a test area first to safeguard against an undesirable outcome. This technical data sheet is merely a guide and not a guarantee. All products are formulated to the best of our knowledge. The information is given as a result of many years experience. This product has had extensive tests carried out.

Produced by Debal Coatings nv

Industrieweg 29 - 8800 Beveren-
Roeselare Belgium tel. +32 (0) 51 30 11 40
fax +32 (0) 51 31 26 48
ciranova@ciranova.be

PRODUCT DESCRIPTION

Water based impregnation oil for parquet and wooden furniture. Only for interior use. In partucularly for interior where a natural finish is needed such as parquet, veneer and other wooden objects

TECHNICAL DATA

Viscosity	+/- 20 sec. (Din 4mm/20°C)
SOLID CONTENTS	+/- 25 % by weight
DENSITY	+/- 1,00 kg/lit.
Gloss	matt
NMP FREE	
CONFORM THE EUROPEAN DECO-PAINT DIRECTIVE 2010	

PREPARATION

Surface: Solid wood, ingeneerd wood. Sand the surface with grain 120 – 150 and afterwards remove sanding dust.

USER TIPS

Use the ECOFIX Ciranova as a sealer and topcoat. Mix the product well before use. After mixing or stirring the product, the product have to rest for 15 minutes before use. Application is done by brush or roller. A short haired roller is prefered. After applying and drying the first coat, sand this coat with grain 280-320. Remove sanding dust and apply a second coat. Repeat and apply a third coat when needed.



DRYING TIMES

Dust free: 20 to 30 minutes

Handling: 1 hour

Sandable: 1 to 2 hours

The drying is strongly depending on the applied quantity, the temperature, air humidity and the ventilation of the room. Through a higher temperature and a good ventilation, drying time is limited.

APPLYING QUANTITY

12 – 14 m²/lt.

AFTERTREATMENT

Follow instructions prescribed by Ciranova.

PRODUCT INFORMATION

12 months in well-closed and original packing.

Warehousing at +5°C – 40°C: not frost-durable.

Danger class VbF: none

Dangerclass GGVS/E: none

SPECIAL QUALITIES

Use only stainless material. After use, since the material directly with water. This product cannot be poured into sewerage. If a stain on the wood is needed, only use AQUACOLOR Ciranova. Be aware of discoloration or detachment because of wood compounds like resins or tanin.