

# Liming paste



1L

As with all wood finishing always do a test area first to safeguard against an undesirable outcome. This technical data sheet is merely a guide and not a guarantee. All products are formulated to the best of our knowledge. The information is given as a result of many years experience. This product has had extensive tests carried out.

**Produced by Debal Coatings nv**

Industrieweg 29 - 8800 Beveren-Roeselare  
Belgium  
tel. +32 (0) 51 30 11 40  
fax +32 (0) 51 31 26 48  
ciranova@ciranova.be

**PRODUCT DESCRIPTION**

Ready to use white paste to whitewash open pore wood.

**TECHNICAL DATA**

DENSITY	1,2
SOLID CONTENT	30%

**USE**

Especially for open grained wood such as oak, ash or elm.

**PREPARATION**

It is advisable to brush out the surface with a steel brush.

**USER TIPS**

Treat the wood before with a thinned (1:1) Ciranova Aquiafix Mono or Aquiafix Project 2K. Sand the wood afterwards with 220 grit sandpaper and apply the white paste with a paint brush and wipe after a few minutes the liming paste of until it gets an equalised surface.



**DRYING TIMES**

Touch dry: 30 minutes (at 20°C). Can be sanded after 1 hour. Can be lacquered after 2 hours.

**AFTER TREATMENT**

Once dry, an Ciranova Aquiafix Mono or Aquiafix Project 2K can be sprayed on top.

**SPECIAL QUALITIES**

This product is environmentally friendly. It is based on rye, wheat and recycled titan white. The solvent is water and linseed oil.